



## Tolerancie hrúbok extrudovaných PE a PP dosák

Platné normy

PE DIN EN ISO 14632 /5/99/

PP DIN EN ISO 15013 /5/99/

<i>Hrúbka dosky</i>	<i>Tolerancia</i>
1 mm	$\pm 0,11$ mm
2 mm	$\pm 0,14$ mm
3 mm	$\pm 0,17$ mm
4 mm	$\pm 0,20$ mm
5 mm	$\pm 0,23$ mm
6 mm	$\pm 0,26$ mm
7 mm	$\pm 0,29$ mm
8 mm	$\pm 0,32$ mm
9 mm	$\pm 0,35$ mm
10 mm	$\pm 0,38$ mm
11 mm	$\pm 0,41$ mm
12 mm	$\pm 0,44$ mm
13 mm	$\pm 0,47$ mm
14 mm	$\pm 0,50$ mm
15 mm	$\pm 0,53$ mm
16 mm	$\pm 0,56$ mm
17 mm	$\pm 0,59$ mm
18 mm	$\pm 0,62$ mm
19 mm	$\pm 0,65$ mm
20 mm	$\pm 0,68$ mm
21 mm	$\pm 0,71$ mm
22 mm	$\pm 0,74$ mm
23 mm	$\pm 0,77$ mm
24 mm	$\pm 0,80$ mm
25 mm	$\pm 0,83$ mm
26 mm	$\pm 0,86$ mm
27 mm	$\pm 0,89$ mm
28 mm	$\pm 0,92$ mm
29 mm	$\pm 0,95$ mm
30 mm	$\pm 0,98$ mm

Obchodný sortiment Remaplast:

Vyžadajte si od nás ponuky aj na polotovary z PVC, PE, PP, PMMA, HiPS, ABS, PA 6, PA 4.6, PA 6.6, PA 6.12, PA 12, POM C, POM H, PET, textitu, Dehonitu, PBT, PC, PPE, PTFE, PVDF, ECTF, PEEK, PPS, PSU, PES, PPSU, PEi, technickej gumy, na tesniace a izolačné materiály, priemyselné hadice a termoformovové tvrdé obalové a blistrové PVC, PP, HiPS, PET fólie.

Tel./fax: + 421 / 263 830 991 - 3

Napíšte nám: [info@remaplast.sk](mailto:info@remaplast.sk)